


3D PLUS Multilayer Zirconia Block



- 6 layers Multilayer color
- From 43% to 57% gradient for transparency
- Strength shows gradient from 700MPa to 1050MPa
- Suitable for anterior, crown and 7 unit bridges



Physical Characteristics

Sintered density	6.07±0.03g/cm ³
Bending Strength	700-1050MPa(Av.)
Transmittance	57%-43%
Hardness	1200HV
Sintering temperature	Recommend 1500°C

Color



Adaptation systems

